



Product Data Sheet

Oil Well Cement (OCG-60)

This product is a high-strength, slow setting gypsum cement, specifically designed for use in the oil well servicing industry. Gypsum oil well cement is custom formulated for use in a thixotropic cement product.

TYPICAL PHYSICAL PROPERTIES:

Use Consistency	40cc/100g
Set Time	50 - 70 minutes
Maximum Expansion (%)	0.4%
Dry Compressive Strength	8,000 psi

GENERAL MIXING INSTRUCTIONS:

Plaster and water are always measured by weight. Using a plaster/water ratio outside the recommended use consistency guidelines will impact the set-time, strength and density of the finished piece.

- Sift plaster into water slowly and evenly.
- Let soak for 1 minute. This allows the gypsum crystals to wet-out, displacing trapped air
- Mix for 2 minutes.